

PRODUCT DATASHEET

SAT1 TAPE

SAT1 is a self-bonding tape composed mainly of a butyl rubber-based adhesive material, which is formed into the shape of tape.

APPLICATION

- For filling up cable joints and branches where it would be difficult to use SAT2
- Continuous operating temperature: -30°C to 70°C
- Short term temperature of 100°C for maximum exposure period of 2 hours

DIMENSIONS AND PACKING QUANTITY

	Packing Quantity		
Thickness (mm)	Width (mm)	Length (m)	(roll/box)
1.0	20	5	100



PROPERTIES

Item		Property	Test Conditions	
Tenisle Strength (n/mm²)		0.5	JIS K 6251	
Elongation (%)		1000		
Heat Resistance	Tensile Strength (n/mm²)	0.7	After 100°C x 96 hr heating JIS K 6257	
	Elongation	1000		
Volume Resistivity (Ω .cm)		1 x 10 ¹⁶	JIS K 6911	
Breakdown Voltage (kV/mm)		30		
Self Adhesiveness		Good	Condition after winding at two-fold elongation and subsequent 5-min elapse time	
Hardness		31	Penetrometer Depth	

Note: The above are measured values, not guaranteed values.

HOW TO USE

Clean adequately the surface of the object, wind the tape half-lapped while peeling off the separator, stretching evenly to the extent that its original width is reduced by about 20%. In case of application to filling portions, form it into an appropriate shape beforehand not to include air in the filling. For use in cold seasons, warm it to around room temperature.

Take care not to leave it under direct sunlight in the summer season, since this makes the separator difficult to be peeled.

Be sure to apply SAT2 for insulation over the surface.

In support of our policy of continuous product improvement we reserve the right to change materials and specifications without notice. Drawings, where used, are not to scale. All dimensions are in millimetres and sizes given are approximate. Where possible, technical MSDS data sheets are made available on the website. All products should be installed and used in accordance with manufacturer's instructions provided. Warning: products may be the subject of registered designs and patents. Refer to website for terms and conditions on warranty.

